

Perlon-Monofil GmbH
 Marketing
 Postfach 10 01 42
 D-41519 Dormagen

| | | | |
|---------------------------------------------------------------------------------------------------------------------------------|---------------------------|-------------------------------------------|---------------------------------------------------|
| Perlon® cabled yarn Type T 211 PA 6 high molecular weight chemically stabilized high mechanical strength | | | Main application Pressfelt (seam felt) |
| Technical data Depend on construction | | | Delivery form |
| Nominal diameter mm | Tenacity cN/tex | Shrinkage in hot air (150 °C) % | Spools |
| 0,20 x 2 x 2 | > = 45 | 7 - 8 | K 2000 DIN 200 DIN 250 |
| 0,20 x 2 x 3 | > = 45 | 7 - 10 | Cones Cylindrical tubes |
| Construction as per request ! | | | |

| | | | |
|-----------------------------|-------------|-------------|-------------|
| Numer and date of issue: | 03: 07/2001 | 04: 06/2004 | 05: 04/2005 |
|-----------------------------|-------------|-------------|-------------|