

Perlon-Monofil GmbH  
 Marketing  
 Postfach 10 01 42  
 D-41519 Dormagen

<b>Perlon® cabled yarn Type T 215</b> PA 6 high molecular weight chemically stabilized high mechanical strength			<b>Main application</b> Pressfelt (seam felt)
<b>Technical data</b> Depend on construction			<b>Packaging</b>
<b>Nominal diameter</b> mm	<b>Tenacity</b> cN/tex	<b>Shrinkage in hot air (150 °C)</b> %	<b>Spools</b>
<b>0,20 x 2 x 2</b>	<b>&gt; = 46</b>	<b>3 - 6</b>	<b>K 2000</b>  <b>DIN 200</b>  <b>DIN 250</b>
<b>0,30 x 1 x 3</b>	<b>&gt; = 45</b>	<b>5 - 7</b>	<b>Cones</b>  <b>Cylindrical tubes</b>
<b>Construction as per request !</b>			

Number and date of issue:	03:07/2001	04: 07/2004	05: 04/2005
------------------------------	------------	-------------	-------------