

Perlon-Monofil GmbH  
 Marketing  
 Postfach 10 01 42  
 D-41519 Dormagen

<b>Cabled yarn Type T 603</b> PA 6.6 providing a high thermal stability			<b>Main application</b> Pressfelt
<b>Technical data</b> Depend on construction			<b>Packaging</b>
<b>Nominal diameter</b> mm	<b>Tenacity</b> cN/tex	<b>Shrinkage in hot air (150°C)</b> %	<b>Spools</b>
<b>0,16 x 2 x 2</b>	<b>&gt; = 45</b>	<b>7 - 9</b>	<b>K 2000</b> <b>DIN 200</b> <b>DIN 250</b>
<b>0,20 x 2 x 2</b>	<b>&gt; = 48</b>	<b>7 - 9</b>	<b>Cones</b> <b>Cylindrical tubes</b>
<b>Construction as per request</b>			

Number and date of issue	03: 07/2001	04: 07/2004	05: 04/2005
-----------------------------	-------------	-------------	-------------