

Perlon-Monofil GmbH
 Marketing
 Postfach 10 01 42
 D-41519 Dormagen

Perlon® Monofilament Type X 205 PA 6 normal molecular weight			Main application Pressing standard
Technical data			Packaging
Nominal diameter mm	Tenacity cN/tex	Shrinkage in hot air (150 °C) %	Spools
0,15	56	4 - 5	K 2000
0,20	56		
0,25	54		
0,35	52	5 - 6	DIN 200
0,40	50		
0,50	50		DIN 250
Additional diameters on request !			

Number and date of issue:	03: 07/2001	04: 07/2004	05: 04/2005
------------------------------	-------------	-------------	-------------