

Perlon-Monofil GmbH
 Marketing
 Postfach 10 01 42
 D-41519 Dormagen

Perlon® Monofilament Type X 211 PA 6 high molecular weight chemically stabilized high tensile and loop strength			Main application Pressing (seam felts)
Technical data			Packaging
Nominal diameter mm	Tenacity cN/tex	Shrinkage in hot air (150 °C) %	Spools
0,15	52,00	9 - 10	K 2000 DIN 200 DIN 250
0,20	52		
0,35	50	10 - 11	
0,40	49		
0,50	48		
Additional diameters on request !			

Number and date of issue:	03: 07/2001	04: 07/2004	05: 04/2005
------------------------------	-------------	-------------	-------------