

Perlon-Monofil GmbH  
 Marketing  
 Postfach 10 01 42  
 D-41519 Dormagen

<b>Perlon® Monofilament Type X 215</b> PA 6 high molecular weight chemically stabilized high tensile and loop strength			<b>Main application</b> Pressing (seam felts)
<b>Technical data</b>			<b>Packaing</b>
<b>Nominal diameter</b> mm	<b>Tenacity</b> cN/tex	<b>Shrinkage in hot air (150 °C)</b> %	<b>Spools</b>
<b>0,20</b>	<b>55</b>	<b>4 - 5</b>	<b>K 2000</b>  <b>DIN 200</b>
<b>0,30</b>	<b>54</b>	<b>5 - 6</b>	<b>DIN 250</b>
<b>Additional diameters on request !</b>			

Number and date of issue:	03: 07/2001	04: 07/2004	05: 04/2005
------------------------------	-------------	-------------	-------------