

Perlon-Monofil GmbH
 Marketing
 Postfach 10 01 42
 D-41519 Dormagen

Perlon Monofilament Type X 224

PA 6 high molecular weight
 chemically stabilized
 medium modulus type
 in line slub and diameter control

Technical data

Nominal diameter mm	Tenacity cN/tex	Shrinkage in hot air (150 °C) %
0,15	40	4 - 5
0,16		
0,17		
0,18		
0,19		
0,20		
0,22		
0,24		
0,25		
0,26		
0,27		
0,28		
0,30		
0,32		
0,35		
0,40	39	5 - 6
0,45	38	
0,50		

Additional diameters on request !

Number and date of issue:	03: 07/2001	04: 07/2004
------------------------------	-------------	-------------

Main application
Forming fabrics

Packaging

Spools

K 2000

DIN 200

DIN 250

05: 04/2005